

NQ COTTON NITROSEL ETH 35%

Packaging

Fiber drum (80 - 136 kg) and cardboard box (20 - 25 kg); please consult us for more detail.

Product Description

Nitrosel is a nitrocellulose type widely used in the production wood coating formulations of primers, sealantes and basecoats.

Recommendations & Benefits

Recommended for use in wood sealers, primers and basecoat formulations, contributing to fast drying, gloss and sandability. Compatible with several resins. Due to the cellulose composition used on Nitrosel manufacture, this product may present more intense color than F-grade nitrocelluloses and also more insoluble particles. In order to obtain better performance of this product we recommend filtering the nitrocellulose solution.

Safety Information

The product safety data sheet is available upon request.

Shelf-Life

Following the handling information correctly, this product has a 12 month shelf-life after its manufacturing date.

Regulatory Information

The product complies with the following regulations:

Europe:

EU N° 10/2011 (Food Contact Materials), Directive 94/62/EC (Heavy Metals).
REACH Substance of Very High Concern - SVHC (Compliance).

United States:

FDA 21 CFR 175.102, 21 CFR 175.300, 21 CFR 176.170, 21 CFR 21 177.1200 (Food Contact Materials).

Brazil and MERCOSUL:

RDC N° 56/2012, RDC N° 91/2001 and RDC 326/2019 ANVISA.
GMC n.32/07, GMC n.02/12 and GMC n.03/92 MERCOSUL.

Product Specification

Property	Range	Unit	A.M.
Viscosity	max. 5,0	sec	PO 4925
Bergmann-Junk Stability	0,0 - 2,5	ml NO/g NC	PO 4931
Nitrogen Content	11,5 - 12,3	%	PO 4927
Solids Content	63 - 67	%	PO 4928
Water Content	0,0 - 7,0	%	PO 4929

Methodologies

The analytical methodologies (A.M.) referred above are available on request.

Transportation, Storage and Handling Information

-Nitrocellulose must be transported and stored in accordance with international standards for dangerous goods;

- Keep the product in a cool, ventilated place, away from sources of ignition or heat;

- Keep the package closed, avoiding the storage or handling of the product outdoors or direct sunlight;

- When handling the product, the packaging must be grounded to dissipate or to avoid generation of static electricity;

- Nitrocellulose is incompatible with alkalis, ammonia, amines, oxidizing agents, etc.

Notice:

Consult the SDS for more details.

The information above is based on our general experience and should be used as a guide. No warranty either expressed or implied is made by Nitro Quimica in this document, which is only a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product and its properties are suitable for a particular purpose. No claim whatsoever may be imposed against us on the basis of the information contained in this publication, or by any information of a technical nature that may subsequently be given. This publication becomes void only if a new edition is published.

(Edition 02/2017)